

an EnerSys company

EnergyCell 1000XLC™

High Capacity Lead Carbon Battery



POWER FLOW

PV SOURCE

PLEXPOWER RADIAN

GRID

GENERATOR

LOAD SUB PANEL

ENERGY STORAGE

- Ideal for high capacity energy demands in off-grid, self-consumption, or emergency backup applications
- 3800 cycles @ 50% DoD at 25°C
- 17 year standby life at 25°C
- High charge acceptance at 300ADC
- 10 year standard full replacement warranty
- Integrated cabinet with modular racking assembly saves on installation time


The EnergyCell XLC battery system is an ideal solution for today's demanding off-grid, self-consumption or backup applications requiring larger energy storage.


The EnergyCell XLC battery system incorporates time-saving modular design. The integrated cabinet with a XLC provides a cost effective solution for all users saving over 40% of installation time compared to a traditional rack. Proven lead-acid VRLA technology, combined with enhanced carbon additives, make it one of the safest batteries in the market. The EnergyCell XLC is unparalleled in performance backed up by a 10-year full replacement warranty (subject to terms and conditions).

The XLC's pioneering lead-acid technology incorporates an added carbon additive to the negative active material (NAM), enhanced separators and anti-corrosion grid design delivering a dramatic improvement in service life. 3800 cycles at 50% DoD, 17 year standby life. Optimized to operate seamlessly with OutBack Power conversion equipment and OPTICS RE connectivity with real-time access to critical battery performance data.

| EnergyCell Model: | 1000XLC* |
|--|--|
| Nominal Voltage Per Cell | 2V |
| Nominal Voltage Per System | ARMIC |
| Cycle Life (50% DoD) | 3800 cycles |
| Absorb Voltage (25°C) | SWIC |
| Absorb Time | 1.2 hours |
| Float Voltage (25°C) | SSTIG SAVOC |
| Float Time | 2 hours |
| Voltage | Equalizer SWIC Re-Bulks (WIC Re-Floats SWIC |
| Maximum Charge Current (Per Battery) | 300ADC |
| Operating Temperature Range (w/Temperature Compensation) | Discharges - 2010 (15010 (-411 1021)) Charges 010 (321 11011) Starages - 2010 (401 1011) |
| Optimal Operating Temperature | 25°C |
| Temp-Comp Factor (Charging) | +5mV/cll/°C |
| Self-Discharge Time | Batteries can be stored up to 6 months at 25°C (77°F) before a freshening charge is required. For higher temperatures the time interval will be shorter. |
| Terminal Type | AND belt |
| Terminal Hardware Initial Torque | 612 KgFcm / 531 LbFin / 60.0 N·m |
| Weight (lb/kg) | 4425.12 / 20072 |
| System Dimensions H x W x D (in/mm) | 67.3 × 44.2 × 21.8 / 1710 × 1125 × 555 |
| Worrenty | 10 year standard warranty ** |
| Accessories | Cabinet, interconnecting bus bars, terminal covers |

| | 2V Ampere Hour Capacity to 1.75 Volts Per Cell at 77°F (25°C) | | | | | | | | | | | | | |
|---------------------|---|-----|-----|-----|-----|-----|-----|-----|-----|------|------|------|--|--|
| Discharge in Hours: | 1 | 2 | 3 | 4 | 5 | 8 | 10 | 12 | 20 | 24 | 48 | 100 | | |
| EnergyCell 1000XLC | 478 | 572 | 642 | 708 | 760 | 824 | 861 | 889 | 972 | 1003 | 1133 | 1230 | | |





 $^{^{\}star}$ Consult local and regional electrical code for proper installation of energy storage requirements.

 $[\]ensuremath{^{\star\star}}\xspace$ Consult EnergyCell XLC warranty documentation for all terms and conditions